

ULTRAPLAN BASIC XTRA – FULL TRANSLATION

CLASSIFICATION ACCORDING TO EN 13813

Complies with EN 13813 CT-C25-F5-A1.

APPLICATION AREA

For interior use to level, smooth and compensate unevenness from 1–10 mm on new or existing substrates.

Suitable for areas with high traffic, chair castors and underfloor heating.

APPLICATION EXAMPLES

- Leveling concrete and cement screeds
- Leveling calcium sulphate screeds
- Heated screed constructions
- Existing substrates such as terrazzo, ceramic and natural stone
- Also suitable for mastic asphalt, chipboard and similar

TECHNICAL CHARACTERISTICS

Self-leveling, fast-hardening compound with excellent flow properties and adhesion.

Can be pumped and applied mechanically up to 100 m distance.

Crack-free application up to 10 mm thickness.

IMPORTANT NOTES

- Do not add water after setting begins
- Do not mix with other binders
- Indoor use only
- Do not use on substrates with rising moisture
- Minimum thickness for parquet: 3 mm

APPLICATION GUIDELINES

Substrate must be clean, dry, solid and free of contaminants.

Priming is always required.

MIXING

25 kg powder with approx. 6–6.5 L water.

Mix to homogeneous compound.

Working time approx. 20 minutes.

APPLICATION

Apply in one operation using trowel or spike roller.

Further layers after approx. 3 hours.

Ready for covering after approx. 24 hours.

CLEANING

Fresh material removable with water, hardened only mechanically.

CONSUMPTION

Approx. 1.6 kg/m² per mm thickness

STORAGE

12 months in dry conditions

SAFETY

Use protective equipment and ensure ventilation.

NOTE

Information based on current knowledge. Application responsibility lies with user.