

PLANIPATCH XTRA – FULL TRANSLATION

CLASSIFICATION ACCORDING TO EN 13813

Leveling compounds with Planipatch Xtra meet classification CT-C35-F7-A1.

APPLICATION AREA

For repair and leveling work to zero thickness on floors, walls, steps and pillars indoors where fast setting and smooth finish are required.

APPLICATION EXAMPLES

- Level uneven substrates to zero
- Fill voids, holes and cracks
- Fast patching before self-leveling compounds
- Repair steps and edges

SUITABLE SUBSTRATES

- Concrete, cement screeds
- Calcium sulphate screeds
- Heated floors
- Tiles, terrazzo, natural stone
- Existing substrates with adhesive residues

TECHNICAL CHARACTERISTICS

Fast-setting, fine, cement-based leveling compound with excellent adhesion and smooth finish.

IMPORTANT NOTES

- Do not add extra water
- Do not mix with other binders
- Indoor use only
- Protect from rapid drying

APPLICATION

Mix 25 kg with approx. 6.3–6.8 L water.

Apply with trowel.

Processing time: approx. 10 minutes.

LAYING TIMES

- 45–60 minutes for patching
- 4–6 hours for full leveling

CONSUMPTION

Approx. 1.4 kg/m² per mm thickness

STORAGE

12 months dry storage

SAFETY

Use protective equipment and ensure ventilation.

NOTE

Data based on current knowledge; no guarantee for specific applications.